

Characteristics

This revolutionary new synthetic material has all of the preferred physical characteristics of natural rubber latex without the natural rubber proteins and allergens. Aqueous gel interior provides superior donning even when hands are damp. White color.



**Surgical Glove
Sterile**

*DermAssist®
Prestige®*

**Polyisoprene
Series 140**



PRODUCT DETAILS

SIZE	ITEM NO.	PACKAGING	DESCRIPTION
5.5	140550	25 pairs/box, 4 boxes/case	Gloves, Surgical, Latex-Free, Sterile, Powder-Free, Smooth Finish, Damp Hand Don
6	140600	25 pairs/box, 4 boxes/case	
6.5	140650	25 pairs/box, 4 boxes/case	
7	140700	25 pairs/box, 4 boxes/case	
7.5	140750	25 pairs/box, 4 boxes/case	
8	140800	25 pairs/box, 4 boxes/case	
8.5	140850	25 pairs/box, 4 boxes/case	
9	140900	25 pairs/box, 4 boxes/case	

Features

- Unique Hydrogel Interior
- Bisque Finish
- Low Modulus
- Non Latex
- Non-Detectable Residual Chemical Level

Benefits

- Damp hand Donnability
- Improved Wet/Dry Grip
- Softer, More Comfortable Fit
- Reduced Chances of Latex Allergic Reactions
- Reduced Chance of Dermatitis and Type IV Reactions

Product Solutions You Trust



DermAssist® Prestige® Polyisoprene POWDER-FREE SURGICAL GLOVES



Product Attributes

- Polymer Coated
- Bisque Finish
- Low Modulus
- Non Latex
- Non-Detectable Residual Chemical Level

Benefits

- Improved Donning Properties
- Improved Wet/Dry Grip
- Greater Tactile Sensitivity
- No Chance of Latex Allergic Reactions
- Reduced Chance of Dermatitis and Type IV Reactions

DermAssist® Prestige® is manufactured in compliance with multiple international standards, including the following:

Designation	Standard
ASTM D3577	Standard Specification for Rubber Surgical Gloves
ASTM D5151	Standard Test Method for Detection of Holes in Medical Gloves
ASTM F1671	Standard Test Method for Resistance of Materials Used in Protective Clothing to Penetration by Blood-Borne Pathogens
ASTM D6319	Standard Specification for Surgical Gloves for Medical Application

Average Length	Average Palm Thickness	Average Finger Thickness
11.6 in ♦ 295 mm	8.0 mil ♦ 0.20 mm	9.8 mil ♦ 0.25 mm

Tensile Strength & Elongation	Before Aging	After Accelerated Aging
Tensile Strength (Mpa)	25	24
ASTM Requirement Min. (Mpa)	17	12
Elongation (%)	850	820
ASTM Requirement Min. (%)	650	490



Intertek

Innovative Healthcare Corporation
is certified to ISO 13485:2003 QMS
for medical devices.



4040 Norex Drive, Chaska MN 55318
phone: 952.448.4412 | fax: 952.448.6180
sales@smithengineeringinc.com
www.smithengineeringinc.com